

ChromaLuxe®

Textured
Aluminum

QUICK GUIDE

ChromaLuxe.com

Our NEW TEXTURED ALUMINUM is an exciting addition to the ChromaLuxe line. With the durability and vibrancy you've come to expect from ChromaLuxe, but with an alternative look that you can actually feel!

FOR MORE INFORMATION VISIT:

STARTTOSUBLIMATE.COM

HEAT PRESS

.....

Ideal settings for sublimating Textured Aluminum are **385°F/195°C**, with **60-70 PSI** and a dwell time starting around **2 minutes**. This recipe is only a general starting point and will vary based on equipment, location, etc.

.....

SUBLIMATION PAPER

.....

Ensure your paper weight is at least **105gsm**. A heavier paper will hold more ink and in turn provide better ink coverage on your print.

.....

IMAGE CONFIGURATION

.....

If adjusted heat press settings and a heavier sublimation paper does not deliver outstanding results, it will be worthwhile to look at your current **ICC profile** or image configuration. It may improve image quality by adjusting the magenta and total ink settings within your RIP software.

.....